GREASE



GREASES FOR INDUSTRIAL USE

CEPSA ARGA LITIO EP EXTREME PRESSURE LITHIUM GREASE

DESCRIPTION

PRODUCT APPLICATIONS

Multipurpose greases prepared for use in all types of bearings and plain bearings, centralized systems and Tecalemit, Stauffer or hand greasers for industrial, marine or automotive equipment subjected to high loads.

- **EP 00**: Mechanisms subjected to high loads and high speeds where a low consistency product is required. Application temperature: -30°C to +90°C (with peaks up to +100°C)
- **EP 0**: Mechanisms subjected to high loads where a low consistency product is required. Application temperature: -30°C to +120°C (with peaks up to +105°C).
- **EP 1**: Mechanisms subjected to high loads in conventional applications, pumping or centralized greasing. Application temperature: -20°C to +120°C (with peaks up to +130°C).
- **EP 2**: Mechanisms subjected to high loads in conventional applications or by pump or centralized lubrication. Application temperature: -20°C to +130°C (with peaks up to +140°C).

PRODUCT PERFORMANCE

- Manufactured greases with highly refined mineral oil, lithium soap and extreme pressure additives.
- Formulating by using additives to provide a good rust protection, anticorrosive, antioxidant and antiwear protection.
- Highly resistant to moisture and practically insoluble in water.

TYPICAL CHARACTERISTICS

| CHARACTERISTICS | UNITS | METHOD | CEPSA ARGA LITIO EP | | | |
|----------------------------------|--------|------------|---------------------|-----------|-----------|-----------|
| | | | EP 00 | EP 0 | EP 1 | EP 2 |
| Colour | | Visual | Brown | Brown | Brown | Brown |
| NLGI consistency | | ASTM D 217 | 00 | 0 | 1 | 2 |
| Type of thickener | | | Lithium | Lithium | Lithium | Lithium |
| Dropping point | °C | ASTM D 566 | >160 | >160 | >185 | >185 |
| Temperature range | °C | | -30 a 90 | -20 a 100 | -20 a 120 | -20 a 130 |
| Penetration 60 strokes | 0,1 mm | ASTM D 217 | 400-430 | 355-385 | 310-340 | 265-295 |
| Base oil | | | Mineral | Mineral | Mineral | Mineral |
| Viscosity at 40°C | cSt | ASTM D 445 | 150 | 150 | 150 | 150 |
| E.P. (4 ball test), Welding load | kg | IP 239 | 300 | 260 | 280 | 280 |
| Classification | | ISO 6743-9 | LX CBEB00 | LX BBEB0 | LX BCHB1 | LX BCHB2 |
| | | DIN 51502 | GP00E-30 | GP0G-20 | KP1K-20 | KP2K-20 |

HEALTH & SAFETY AND ENVIRONMENT

Health, safety and environmental information is provided for this product in the Materials Safety Data Sheet. This gives details of potential hazards, precautions and First Aid measures together with environmental effects and disposal of used products.

The typical values of the characteristics appearing in the table are average values given for guidance purposes. These values may be modified without any prior warning.